

SC-430S

Features

- Cored wire for submerged arc hardfacing (build-up)
- Ferritic stainless steel type
- SAW(with S-717/S-401HF flux)

Polarity

DC +

Application Areas

- Continuous casting rolls, steel mill rolls

Shielding Gas

None

Typical Chemical Composition of All-Weld Metal (wt%)

Wire size	C	Si	Mn	Cr
3.2(1/8)	0.06	0.9	1.5	17.0

Typical Mechanical Properties of All-Weld Metal

Item	HRC (≥4Layers)
S-717	5~10

Diameter / Welding Parameters / Packaging

Wire Diameter mm(in)	Current (A)
3.2(1/8)	350~450

Diameter / Welding Parameters / Packaging

Wire Diameter mm(in)	Packaging
2.4(3/32)	Coil 25kg(55lbs), Drum 150kg, 250kg
3.2(1/8)	