

S-308.16N

Classification

- AWS** A5.4/ASME SFA-5.4 E308-16
- JIS** Z 3221 ES308-16
- EN** ISO 3581- A E 19 9 R
- KS** D7014 E308-16

Welding Positions



Features

- Good resistance to corrosion and oxidizing environments
- Easy to remove slag
- Low spatter
- Good bead appearance

Polarity

AC or DC+

Application Areas

- Stainless steel (18%Cr-8%Ni)

Redrying Conditions

350°C (662°F) X 1hr

Approvals

ABS	DNV	KR
✓	✓	✓

Typical Chemical Composition of All-Weld Metal (wt%)

C	Si	Mn	P	S	Cu	Ni	Cr	Mo
0.04	0.57	0.8	0.027	0.018	0.04	10.1	18.4	0.04

Typical Mechanical Properties of All-Weld Metal

Tensile Strength MPa(ksi)	Elongation (%)	Temperature °C (°F)	Impact Toughness J (ft·lbs)
570(83)	44	-60(-75)	43(32)

SMAW

GTAW

FCAW

Metal-cored Wire

SAW Wire

SAW Flux

Diameter / Welding Parameters / Packaging

Diameter mm(in)	Length mm(in)	F & HF	V-up, OH	Packaging
2.0 (5/64)	300 (12)	25~55	20~50	PVC - Packet 2.5kg(5.5lbs), Carton 10kg (22lbs)
2.6 (3/32)	300 (12)	50~85	45~80	
3.2 (1/8)	350 (14)	70~115	65~110	
4.0 (5/32)	350 (14)	95~145	85~135	
5.0 (3/16)	350 (14)	135~180	-	

SMW

GMAW

GTAW

FCAW

Metal-cored Wire

SAW Wire

SAW Flux