


S-7018.A1

Classification

AWS A5.5/ASME SFA-5.5 E7018-A1
JIS Z 3223 E4918-1M3
EN ISO 3580-A E Mo B 3 2

Welding Positions



Features

- Good mechanical properties
- Good bead appearance
- Iron powder type electrode (high efficiency)

Polarity

AC, DC ±

Application Areas

- Low alloy steel (0.5% Mo)
- Pressure vessels

Redrying Conditions

300~350°C (572~662°F) X 0.5~1hr

Typical Chemical Composition of All-Weld Metal (wt%)

C	Si	Mn	P	S	Mo
0.05	0.65	0.70	0.016	0.007	0.51

Typical Mechanical Properties of All-Weld Metal

PWHT	Yield Strength MPa(ksi)	Tensile Strength MPa(ksi)	Elongation (%)
620°C*1hr	525(76)	627(91)	31

Diameter / Welding Parameters / Packaging

Diameter mm(in)	Length mm(in)	F & HF	V-up, OH	Packaging
2.6 (3/32)	350 (14)	55~90	50~80	Standard/Vacuum - Packet 5kg (11lbs), Carton 20kg (44lbs)
3.2 (1/8)	350 (14)	90~130	80~120	
4.0 (5/32)	400 (16)	130~190	120~170	
5.0 (3/16)	400 (16)	190~240	-	
6.0 (15/64)	450 (18)	250~300	-	

SMAW

GMAW

GTAW

FCAW

Metal-cored Wire

SAW Wire

SAW Flux